

STABURAGS NBU 8 EP

Rolling bearing and high-pressure grease



Benefits for your application

- **Good corrosion protection**
- **Good resistance to ambient media**
- **Good wear protection / EP properties**
- **Protects against tribo-corrosion**
- **High-pressure grease**

Description

STABURAGS NBU 8 EP is a lubricating grease based on mineral oil and barium complex soap. It has been used successfully for many years as a long-term grease for bearings subject to high specific loads. Its good wear protection properties are enhanced by the barium complex thickener. STABURAGS NBU 8 EP protects reliably against corrosion and is resistant to water. It meets the requirements of DIN 51 807, dated May 1970: SKF-R2F test, test run B, 140 °C, and it achieves about 4000 operating hours in the SKF-ROF test at 120 °C.

Application

STABURAGS NBU 8 EP has proven efficient as a rolling bearing and high pressure grease protecting against wear. It is used in

traction motors, journal bearings, electric motors, pumps, and tapered roller bearings.

Application notes

The product is applied by brush, spatula or conventional metering systems.

Material safety data sheets

Material safety data sheets can be downloaded or requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	STABURAGS NBU 8 EP
Cartridge 400 g	+
Can 1 kg	+
Bucket 25 kg	+



STABURAGS NBU 8 EP

Rolling bearing and high-pressure grease

Product data	STABURAGS NBU 8 EP
Article number	017105
Lower service temperature	-20 °C / -4 °F
Upper service temperature	140 °C / 284 °F
Speed factor (n x dm)	approx. 500 000 mm/min
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	295 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	265 x 0.1 mm
NLGI grade, DIN 51818	2
Kinematic viscosity, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 11.5 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 97 mm ² /s
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, upper limit value	9 500 mPas
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	5 500 mPas
Drop point, DIN ISO 2176	>= 220 °C
Density at 20 °C	approx. 0.99 g/cm ³
Colour space	brown
Chemical composition, thickener	barium complex soap
Chemical composition, type of oil	mineral oil
NSF-H2 registration	135 684
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.



a company of the Freudenberg Group